TWO COLOURS



ONE DIRECTION

Polyethylene TIPELIN BA 550-13

HDPE for blow moulding

Description

TIPELIN BA 550-13 is a high density polyethylene copolymer (with hexen-1 as comonomer) grade for blow moulding of products which require good chemical resistance, furthermore high rigidity. The grade contains antioxidant and acid scavenger.

Applications

TIPELIN BA 550-13 is recommended for bottles and cans up to 30 litre capacity for non aggressive household chemicals, cosmetics and oils. The product is suitable for non-pressure pipes too.

TIPELIN BA 550-13 is suitable for food contact, for manufacturing of pharmaceutical packing products and toys. The product complies with Food Contact, Pharmaceutical and Toy Safety Regulations.

Properties

	Test method	Unit	Typical value
Melt Mass-Flow Rate (MFR) (190 °C /2.16 kg)	ISO 1133	g/10 min	0.35
Density (23 °C) *	ISO 1183	kg/m ³	955
Tensile Strength at Yield *	ISO 527-1,2	MPa	29
Tensile Strain at Break *	ISO 527-1,2	%	1100
Flexural Modulus *	ISO 178	MPa	1450
IZOD Impact Strength (notched, 23 °C) *	ISO 180/1A	kJ/m²	13
Vicat Softening Temperature *	ISO 306/A 120	℃	129
Shore D Hardness *	ISO 868	-	65
ESCR F50 B (100% Igepal CO-630) *	ASTM D 1693	h	55
OIT (200 °C) *	EN 728	min	8

Typical properties, not to be used as specification.

* Average mechanical properties:

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN





^{*} Average mechanical property values of several measurements carried out on standard pressed specimens (ISO 293) conditioned at room temperature (ISO 291).



Processing

TIPELIN BA 550-13 can be used in conventional blow moulding machines. Recommended processing temperature 180-220 °C.

Storage and Handling

Pellets are packed in 25 kg PE-LD bags and transported on stretch-wrapped pallets at load of polymer 1375 kg. Heat treated pallets are available as well. Transportation in a road silo or rail silo is also available. For more detailed information please contact Slovnaft Petrochemicals and TVK sales representative.

Since polyethylene is a combustible substance, the fire safety rules applicable for combustible materials in warehouses and store rooms should be observed.

If polymer is stored in conditions of high humidity and fluctuating temperatures, then atmospheric moisture can condense inside the packing. If it happened, it is recommended the pellets to be dried before use. During the storage polyethylene should not be exposed to UV radiation. Producer does not take responsibility for any damages caused by adverse storage.

REACH Statement

Polymers are exempt of REACH registration. However their raw materials which mean monomers, catalysts and most additives have been preregistered. SPC/TVK is committed to fully respect this new legislation and will only use REACH compliant raw materials. At this point in time SPC/TVK polyethylenes TIPELIN do not contain any substances specifically identified as SVHC at levels greater than 0.1%.

Safety

See MSDS.

Recycling

Polyethylene resins are suitable for recycling using modern recycling methods.

In-house production waste should be kept clean to facilitate direct recycling.

Disclaimer

The information provided in this publication has been compiled to the best of our present knowledge. However, in view of the various applications of polyethylene resins and the equipments used, the processing conditions may differ.

The recommendations and data herein are to be construed as informatory only and do not relieve users from carrying out their own tests and experiments prior to processing in order to check suitability for a specific use. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. Our products are under continuous development, therefore we reserve the right to change the information presented in this brochure at our own discretion. The REACH statement herein does not constitute legal advice. The REACH statement is provided for informational purpose only.

TIPELIN TIPOLEN TIPPLEN TATREN **BRALEN**





MANUFACTURER

TVK Plc.

H-3581 Tiszaújváros,

P.O. Box: 20 Hungary

Internet: www.tvk.hu
E-mail: tvkinfo@tvk.hu

TECHNICAL SERVICE

TVK Plc.

Polymer Marketing and Sales

Technical Service

H-3581 Tiszaújváros,

P.O. Box: 20 Hungary

Fax: + 36 49 521-186

E-mail: customerservice@tvk.hu

Technical service for PE

Telephone: + 36 49 521-367, + 36-80 204-249,

Technical service for PP

Telephone: + 36 49 522-013, + 36-80 204-248

SALES ORGANIZATION

TVK Plc.

Polymer Marketing and Sales Department

H-3581 Tiszaújváros,

P.O. Box: 20 Hungary

Telephone: +36 49 521-355 Fax: +36 49 522-410

E-mail: polymersales@tvk.hu

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN





TVK Inter-Chemol GmbH.

Fellnerstrasse 7-9. D-60322 Frankfurt am Main Germany

Telephone: +49 69 154 04 12

+49 69 154 04 31

Fax: +49 69 154 04 41 E-mail: gaboragoston@tvkic.de

andrasvarnai@tvkic.de

TVK Italia S.r.L.

Via P. Teulié 1. I-20136 Milano Italy

Telephone: +39 02 58 30 5523 Fax: +39 02 58 30 3492

E-mail: tvkitaly@energy.it

TVK-France

182 Avenue Charles DeGaulle F-92200 Neuilly-sur-Seine

France

Telephone: +33 14 745 63 60 Fax: +33 14 745 45 10 E-mail: tvk.france@orange.fr

TVK Ukraine

04128 Kiev

ul. Tupoleva, 19, office 303
Telephone: +380 44 374 00 80
Fax: +380 44 374 00 90
E-mail: gnatalia@tvkukraine.eu

TVK Polska Sp. z o.o.

ul. Wawozowa 23/12 PL 02-796 Warszawa

Poland

Telephone: +48 22 545 70 70 Fax: +48 22 545 70 60 E-mail: tvkpolska@tvkpolska.pl

www.tvkpolska.pl

MOL- Austria Handels GmbH.

Gartenbaupromenade 2/6 A-1010 Wien

Austria

Telephone: +43 1 515 991 120

+43 1 515 991 121

Fax: +43 1 513 37 55 1120

+43 1 513 37 55 1121

E-mail: JHauk@MOL.hu

SC. MOL Romania P.P. SRL

Str. Danielopolu 4-6 ET2 Sector 1 Cod 014 134

Bucuresti, Romania

Telephone: +40 21 204 85 00

+40 21 204 85 02

Fax: +40 21 232 1059 E-mail: ematei@molromania.ro

petchem@molromania.ro

Other European Countries

H-3581 Tiszaújváros

P.O.B. 20.

Telephone: +36 49 521 162 Fax: +36 49 522 410 E-mail: bpetra@tvk.hu

May 2010

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

